

FJSRL-TR-88-0003

FRANK J. SEILER RESEARCH LABORATORY

Viscosity and Conductance
of MEICI/AICI₃ MeIts
Containing Nonaqueous Solvents
DTIC

ELECTE MAR 2 0 1980

C. J. Dymek, Jr. and G. E. Godec

APPROVED FOR PUBLIC RELEASE;
DISTRIBUTION UNLIMITED.

May 1988

AIR FORCE SYSTEMS COMMAND

UNITED STATES AIR FORCE

89 3 20 068



FJSRL-TR-88-0003

This document was prepared by the Electrochemistry Division, Directorate of Chemical Sciences, Frank J. Seiler Research Laboratory, United States Air Force Academy, CO. The research was conducted under Project Work Unit number 2303-F2-10. Lt Col Chester J. Dymek, Jr. was the project scientist.

When U.S. Government drawings, specifications, or other data are used for any purpose other than a definitely related government procurement operation, the government thereby incurs no responsibility nor any obligation whatsoever, and the fact that the government may have formulated, furnished or in any way supplied the said drawings, specifications or other data is not to be regarded by implication or otherwise, as in any manner licensing the holder or any other person or corporation or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.

Inquiries concerning the technical content of this document should be addressed to the Frank J. Seiler Research Laboratory (AFSC), FJSRL/NC, USAF Academy, Colorado Springs, CO 80840. Phone AC 303-472-2655.

This report has been reviewed by the Commander and is releasable to the National Technical Information Service (NTIS). At NTIS it will be available to the general public, including foreign nations.

This technical report has been reviewed and is approved for publication.

CHESTER J. DYMER, UR., Lt Col., USAF

. . .

STEPHEN W. LANDER JR., Lt Coy, I

Director, Chemical Sciences

Senior Scientist

KENNETH E. SIEGENTHALER, Lt Col, USAF

Chief Scientist

Copies of this report should not be returned unless return is required by security considerations, contractural obligations, or notice on a specific document.

Printed in the United States of America. Qualified requestors may obtain additional copies from the Defense Documentation Center. All others should apply to:

National Technical Information Service 6285 Port Royal Road Springfield VA 22161

ECURITY CLASSIFICATION OF THIS PAGE	REPORT DOCUME	NTATION PAGE	*						
18 REPORT SECURITY CLASSIFICATION Unclassified		1b. RESTRICTIVE MARKINGS							
28. SECURITY CLASSIFICATION AUTHORITY		3 DISTRIBUTION/AVAILABILITY OF REPORT Approved for public release; distribution							
26. DECLASSIFICATION/DOWNGRADING SCHEDULE		unlimited.							
4. PERFORMING ORGANIZATION REPORT NUM FJSRL-TR-88-0003	BER(S)	5. MONITORING OR	GANIZATION RE	PORT NUMBER	5)				
6a NAME OF PERFORMING ORGANIZATION Frank J. Seiler Research Laboratory	6b. OFFICE SYMBOL (If applicable) FJSRL/NC	78. NAME OF MONI	TORING ORGANI	ZATION					
Bc. ADDRESS (City, State and ZIP Code) USAF Academy Colorado Springs CO 80840-6		7b. ADDRESS (City)	State and ZIP Cod	c)					
e name of funding/sponsoring organization AF Office of Scientific Research	8b. OFFICE SYMBOL (If applicable) AFOSR	9. PROCUREMENT I	INSTRUMENT IDE	ENTIFICATION N	UMBER				
Bc. ADDRESS (City, State and ZIP Code)	Arosk	10. SOURCE OF FU	NDING NOS						
Bldg. 410 Bolling AFB DC 20332		PROGRAM ELEMENT NO	PROJECT NO.	TASK NO.	WORK UNIT				
11. TITLE (Include Security Classification) Visco ance of MEICI/AICI3 Melts Conta	sity & Conduct- ining Nonaqueous	61102F	2303	F2	10				
12. PERSONAL AUTHOR(S) Chester J. Dymek, Jr. and Greg 13a. TYPE OF REPORT 13b. TIME C		14. DATE OF REPO 88/05/2		15 PAGE (COUNT				
FIELD GROUP SUB. GR. 10 02 07 04 ABSTRACT (Continue on reverse if necessary and	18. SUBJECT TERMS (C) imidazolium, to viscosity, (c)	nolten salt,	chloroalumí	nate, condu	ctance,				
Ionic liquids formed by mixing are of interest as electrolyte were observed upon addition of Conductivities and viscosities tion of mole fraction of solve model for benzene-ion and ion-the variations in the interdepsolutions.	s 1-methyl-3-ethy es for batteries. The solvents, he s of these melt/s ent and found to ion interactions bendence of condu	viimidazolium Enhanced con enzene, aceto solvent soluti have similar in the solu- ictivity and	onductiviti onitrile, a ions were m functional tions is pr viscosity i	es of these nd dichloro easured as dependence oposed to e n the benze	melts methane. a func A xplain				
20 DISTRIBUTION/AVAILABILITY OF ABSTRA		21. ABSTRACT SEC		ICATION					
UNCLASSIFIED/UNLIMITED X SAME AS APT	LI DEIC USERS LI	Unclassifi	NUMBER	22c OFFICE SY	MBOL				
Chester J. Dymek, Jr.		(Include Area C		FJSRL/NC	;				

VISCOSITY AND CONDUCTANCE OF MEIC1/A1C13 MELTS CONTAINING NONAQUEOUS SOLVENTS

Ву

Chester J. Dymek, Jr.

and

Greg E. Godec

May 1988

Approved for public release; distribution unlimited.

Directorate of Chemical Sciences

The Frank J. Seiler Research Laboratory

Air Force Systems Command

TABLE OF CONTENTS

SUMMARY	•	•		•	•	•	•	•	•	•	•	•	•	•	•	•	٠	•	•	•	•	•	•	•	•	•	•	•	•	•	•	1
INTRODUCTIO	N					•	•		•			•	•			•	•	•	•						•			•	•	•		Ź
EXPERIMENTA	L			•	•		•		•	•	•	•	•	•	•	•		•	•	•	•	•	•	•		•	•	•	•	•		ā
RESULTS AND	DI	SC	uss	ION	i		•	•	•	•	•				•	•		•		•		•		•	•	•	•		•	•		3
REFERENCES																																12

Accession For	r
NTIS GRAZI	
DTIC TAR	
- Unaumouliced	П
វិធន នេះ 🗽 🔭	P
Distribution Av- Cable to Av	/ y nodes mod/or
	1883

SUMMARY

Ionic liquids formed by mixing 1-methyl-3-ethylimidazolium chloride (MEIC1) with AlCl₃ are of interest as electrolytes for batteries. Enhanced conductivities of these melts were observed upon addition of the solvents, benzene, acetonitrile, and dichloromethane. Conductivities and viscosities of these melt/solvent solutions were measured as a function of mole fraction of solvent and found to have similar functional dependence. A model for benzeneion and ion-ion interactions in the solutions is proposed to explain the variations in the interdependence of conductivity and viscosity in the benzene-melt solutions.

INTRODUCTION

Ionic liquids formed by mixing 1-methyl-3-ethylimidazolium chloride

(MEIC1) with AlC13 are of interest as electrolytes for batteries because they are nonaqueous media with relatively high conductance at and below room temperature (1)(2). It was found that the specific conductance of basic melts (with mole fraction, N, of AlC13 less than 0.5) could be increased by the addition of benzene (3). A plausible explanation for this phenomenon is that benzene interacts with the MEI* in such a way as to reduce the interionic attractions, thereby making the ions more mobile. The question of whether this is equivalent to an explanation which has the mobility increasing due to decreasing viscosity is the subject of the work reported here. We investigated the dependence of equivalent conductance and fluidity (i.e. inverse of viscosity) on mole fraction of added solvent for three non-aqueous solvents of varying dielectric constant to explore this question.

EXPERIMENTAL

MEIC1 and AlC13 were prepared and purified as previously reported (4). Acetonitrile (OMNI SOLVE grade) was distilled over P_2O_5 for two days. Dichloromethane (Aldrich HPLC grade) was distilled over $CaCO_3$ for two days. Benzene (Kodak reagent grade) was distilled over $CaCO_3$ for two days. Melts of MEIC1/AlC13 with $\underline{N}=0.48$ were prepared in a dry box with a helium atmosphere with less than 10 ppm H_2O/air . Melt/solvent solutions were also prepared in the dry box using their weights in closed containers to determine composition. Volumes used to obtain molarity for equivalent conductance determina-

tions were calculated from solution densities. Densities were determined using a Mettler DMA40 Digital Density Meter. Conductances were measured using a YSI model 3402 dips conductivity cell (k = 1.0 cm⁻¹) inserted in a closed flask containing the solutions of known composition. Measurements were made at 1000 kHz using a YSI Model 31A Conductance Bridge. Kinematic viscosity measurements were made immediately after the conductance measurement had stabilized using a Lauda model B viscometer and KPG-Ubbelode viscometry tubes. Kinematic viscosities were converted to absolute viscosities using the measured densities. All measurements except density were performed in the He-filled dry box at 28 ± 1°C.

RESULTS AND DISCUSSION

Equivalent conductances were calculated using the number of moles of MEI⁺ as the number of moles of salt present, with AlCl₄⁻ and Cl⁻ as the anions. Specific conductances shown in Tables 1, 2, and 3 were recorded after readings had completely stabilized, usually in at least 15 minutes. The viscosities reported are the averages of at least three runs each. The solutions measured were prepared by successive dilutions of the N = 0.48 melt with weights measured in closed containers to minimize errors due to solvent evaporation.

Plots of equivalent conductance (in Scm^2mol^{-1}) and fluidity (in cP^{-1}) vs mole fraction of solvent added to the $\underline{N}=0.48$ melts are shown in Figures 1, 2, and 3. The dilutions continued until the appearance of a second phase was observed. For benzene this occurred at about mole fraction of benzene of 0.78 and for dichloromethane, at mole fraction of dichloromethane of 0.90. Acetonitrile was completely miscible with $\underline{N}=0.48$ melt at $28^{\circ}C$.

Table 1
Viscosity and Conductance of
MEICL/ALCL 8 Melts Containing :cetonitrile

Mo1%	Density	Mo1/1	Fluidity	
0	1.263	4.677	. 048	-
30	1.204	4.456	. 118	
45	1.182	4.375	. 182	
50	1.704	4.280	. 209	
60	1.140	4.218	299	
65	1.265	4.120	352	
70	1.107	4.000	.471	
80	1.051	3.890	. 679	
85	1.011	3.667	. 963	
90	. 951	3.518	1.245	
92	. 928		1.516	

Mai %	•	Equivalent Conductance
0.0	. 0172	3.604
13.0	0211	4.574
26.3	0256	5.826
40.3	.0339	8.248
62.8	0461	13.659
72.3	.0588	20.137
77.0	0645	24.441
85.7	. 0645	33.247
89.2	0690	43.616
93.0	. 0578	51.699
95.1	0541	65.417
97.5	0368	83.070

Table 2
Viscosity and Conductance of MEIC1/AlC1₃
Melts Containing Benzene

			•	
Mol %	Density g/mi (Specific Conductance	Equvalent Conductance	Fluidity
0.0	1.25	0185	3.99	. 0557
21.7	1.43	. 0227	5.28	.0818
39.3	1.21	. 0250	6.56	. 1199
47.2	1.14	. 0272	7.75	. 1395
58.0	1.06	. 0287	9.29	. 1901
71 8	1.00	. 0290	12.24	. 2882
74.6	0.99	. 0279	12.68	3135
78. Q	0.98	. 0264	13.33	3630

Table 3
Viscosity and Conductance of MEIC1/AlC1₃
Melts Containing Dichloromethane

Mol %		Mol/l [MEI*]		Specific Conductance	Fluidity CP
0	1.283	4.765	0190	3.620	0499
30	1.290	4.225	.0227	5.386	. 0951
45	1.293	3.817	0270	7.079	1398
60*			0323	9.835	
65*			.0331	10.681	
65	1.309	3.088	0330	10.687	2603
67*			.0332	11.455	
70	1.310	2.794	0332	11.891	3122
70*			.0333	11.903	
72*			. 0333	12.808	
75*			. 0333	13.660	
75	1.317		. 0323	13.658	3691
78*			. 0331	14.716	
80	1.318	2.164	. 0323	14.935	.4626
85	1.319	1.757	. 0296	16.842	6158
90	1.319	1.276	. 0226	17.727	8970

^{*}Second data set




Figure 1. Equivalent Conductance and Fluidity of N=0.48 Melt as a Function of Mol Fraction of Added Benzene.




Figure 2. Equivalent Conductance and Fluidity of N≈0.48 Melt as a Function of Mol Fraction of Added Acetonitrile.




Figure 3. Equivalent Conductance and Fluidity of N=0.48 Melt as a Function of Mol Fraction of Added Dichloromethane.

Over the range of mole fraction of solvent added in which they can be compared, there is little difference in the fluidity or equivalent conductances for the three solutions. What is clear from the results is that the equivalent conductance has very nearly the same functional dependence on mole fraction of solvent added as does the fluidity. Dichloromethane shows the most obvious deviation from this behavior, an observation which prompted a second run for this system as show in Figure 3. In benzene and dichloromethane solutions, as the limit of miscibility is approached, the equivalent conductance curve starts to turn over relative to the fluidity curve. This suggests that the formation of ion pairs or clusters of ion pairs is beginning to occur as this limit is reached. However, it is clear that the viscosity of the solutions is the primary factor determining the equivalent conductance over most of the range of miscibility. Thus the increased conductivity of melts with these solvents added can be attributed primarily to their increased fluidity. This in turn is attributable to the breaking up of strong interionic attractions by the added solvents. How these solvents "solvate" the MEIt, Clt, and $AlCl_4$ ions is the subject of other ongoing work in this laboratory.

We now propose a model of what is occurring in the melt as benzene is added. In Figure 4, benzene and MEI⁺ are both shown only in end-on positions to simplify the drawings and to emphasize how benzene and MEI⁺ interact. Of course, in a melt the orientations of both would be random, although some transitory short-range structure surely exists. The saw-toothed lines represent attractive interactions between ions. The four stages shown in Figure 4 are briefly described:




Figure 4. Proposed Model Showing Effect of Added Benzene on Melt Equivalent Conductivity and Fluidity.

- 1. With no benzene present, the mobility of the ions is limited by the attractive forces they experience from the extended ionic cage which surrounds them. Both fluidity and equivalent conductance are at a minimum.
- 2. At low concentrations of benzene, the benzene molecules "solvate" the MEI⁺ ions whose interactions with surrounding anions are therefore reduced, leading to increased mobility of both MEI⁺ and the anions. Thus both fluidity and equivalent conductance increase.
- 3. After two benzene molecules for each MEI* present have been added (mol fraction benzene of 0.67), additional benzene is now solvating not just MEI* but also ion-pairs or neutral clusters of ion-pairs as well as charged clusters. This process reduces the number of charge carriers available in the melt solution while at the same time it continues to reduce interactions between ions or charged clusters of opposite charge. Thus the equivalent conductance begins to decrease due to the reduced number of charge carriers even though fluidity increases due to the reduction in interionic attractions.
- 4. Finally a point is researched at which additional benzene is shielded from interaction with MEI* or other benzene molecules which are solvating MEI*. The normal intermolecular forces of pure benzene force this additional benzene into a second phase as indicated by the dashed line in Figure 4.4.

REFERENCES

- Fannin, A. A., Jr.; Floreani, D. A.; King, L. A.; Landers, J. S.; Piersma,
 B. J.; Stech, D. J.; Vaughn, R. L.; Wilkes, J. S.; Williams, J. L.; J. Phys.
 Chem., 88, 2614 (1984).
- 2. Fannin, A. A., Jr.; King, L. A.; Levisky, J. A.; and Wilkes, J. S.; J. Phys. Chem., 88, 2609 (1984).
- 3. Wilkes, J. S., The Frank J. Seiler Research Laboratory, U.S. Air Force Academy, CO 80840, unpublished data.